

Legeringen tabel

| LEGERING EN-AW | NAAM | OUDE NAAMGEVING | WERKSTOF NR. | STAF | PLAAT |
|----------------------------|--------------|-----------------|--------------|------|-------|
| WALS LEGERINGEN | | | | | |
| 1050A | Al99,5 | Al99,5 | 3.0255 | | X |
| 2017A | AlCu4MgSi(A) | AlCuMg1 | 3,1325 | | X |
| 2024 | AlCu4Mg1 | AlCuMg2 | 3,1355 | | X |
| 2618A | AlCu2Mg1,5Ni | AlCu2Mg1,5Ni | 3,1924 | X | X |
| 5083 | AlMg4,5Mn0,7 | AlMg4,5Mn | 3,3547 | X | X |
| 5754 | AlMg3 | AlMg3 | 3,3535 | X | X |
| 6061 | AlMg1SiCu | AlMg1SiCu | 3,3211 | X | X |
| 6082 | AlSi1MgMn | AlMgSi1 | 3,2315 | X | X |
| 7019 | AlZn4Mg2Mn | AlZn4Mg2Mn | | | X |
| 7020 | AlZn4,5Mg1 | AlZn4,5Mg1 | 3,4335 | | X |
| 7022 | AlZn5Mg3Cu | AlZnMgCu0,5 | 3,4345 | X | X |
| 7075 | AlZn5,5MgCu | AlZnMgCu1,5 | 3,4365 | X | X |
| GEGOTEN LEGERINGEN | | | | | |
| 5083C | AlMg4,5Mn0,7 | AlMg4,5Mn | 3,3547 | | X |
| 7021C | AlZn5,5Mg1,5 | AlZn5,5Mg1,5 | | | X |
| EXTRUSIE LEGERINGEN | | | | | |
| 2007 | AlCu4PbMgMn | AlCuMgPb | 3,1645 | X | |
| 2011 | AlCu6BiPb | AlCuBiPb | 3,1655 | X | |
| 6012 | AlMgSiPb | AlMgSiPb | 3,0615 | X | |
| 6026 | AlSiMnMgBi | AlSiMnMgBi | | X | |
| 6060 | AlMgSiPb | AlMgSi0,5 | 3,3206 | X | |
| 6082 | AlSi1MgMn | AlMgSi1 | 3,2315 | X | X |